



## MICROCONE RGL 60

Fiber reinforced micro concrete RCC repairing works with high workability

### Description

**MICROCONE RGL60** is supplied as a ready to use blend of dry powder, which requires only the site addition of clean water to produce a free-flowing, non-shrink micro concrete. The material is based on Portland cements, and fillers, and additives which impart controlled expansion characteristics in the plastic state, while minimizing water demand. The low water requirement ensures high early strength and long-term durability

### Advantages

- Gaseous expansion system compensates for shrinkage and settlement in the plastic state.
- Can be pumped or poured into restricted locations.
- Highly fluid to allow for placement without vibration.
- Pre-packed to overcome site-batched variations.
- Low permeability
- Economical
- Contains no chloride
- Ease of use

### Uses

- For repairs to damaged reinforced concrete elements particularly where access is restricted and where vibration of the placed material is difficult or impossible
- Suitable for various structural strengthening measures such as filling honeycombs and cracks

### Compliance standard:

- DIN 1048 part-5
- BS 6319 pt. 3
- BS 1881 pt.1161 & pt. 122

## Technical Information

PROPERTIES	RESULTS
Appearance	Powder
Color	Grey
Expansion in % by volume	0.8 to 1.5
Wet Density	2100 to 2150 Kg/m <sup>3</sup>

## Application Instruction

- Defective concrete surfaces must be cut back to a sound base than smooth surfaces should be mechanically roughened.
- Corroded reinforcing steel should be exposed around its full circumference and cleaned to remove all loose scale and corrosion deposits. It is important to clean the steel to a bright condition. Grit-blasting is recommended.
- Immediately prior to placing, any free water should be removed.
- Care should be taken to ensure that MICROCONE RGL60 is thoroughly mixed in a forced-action mixer of adequate capacity. The quantity water required will generally be between 4 to 4.5 liters per 25 kg bag of MICROCONE RGL60. After thorough mixing place directly in form work. Slurry tight form work that should not deform or leak when subjected to hydraulic pressure imposed by the micro concrete will be fabricated.

## Compressive strength table

Compressive strength Kg/cm <sup>2</sup>		
Strength checked after Days	Water / powder 0.18 (flowable)	Water/powder 0.16 (flowable)
1 day	150	200
3 days	375	400
7 days	400	500
28 days	550	650

## Placing

- The mixed material should be placed immediately. If placed by pump, standard concrete pumping practice should be followed. The pump and pipeline must be primed with cement slurry. Pumping should be commenced immediately after priming. If poured in the form work, avoid air entrapment by pouring from one side only.

## Low temperature working

- In cold conditions down to 15°C, the use of warm water (up to 30°C) is advisable to accelerate strength development. Normal precautions for working with cementitious materials in winter should be adopted.

## High temperature working

- At ambient temperature above 35°C the material should be stored in the shade and cold water used for mixing.

## Curing:

- As MICROCONE RGL60 is a cement-based repair material, it must be cured immediately after stripping the formwork in accordance with good concrete practice.

## Packaging:

- MICROCONE RGL60 is supplied in 25 kg bags.

## Shelf life:

- MICROCONE RGL60 has a shelf life of 12 months if kept in a dry store in the original, unopened bags. If stored at high temperatures or high humidity conditions the shelf life may be reduced.

## REDWOP CHEMICALS PVT. LTD.

Head office: 2nd Floor, Pearl plaza Complex, B/S GT Sheth School, Near KKV Hall, 150ft Ring Road, Rajkot- Pin.360005 Gujarat, India.

✉ info@redwop.net

🌐 www.redwop.net

☎ +91 97246 55551

☎ +91 281 2576664